

Spin-on-Glass P-280

Elements of Interest Si, O, P	Key Element atoms/cm³ P, 1.9×10^{22}	Key Element % in Film Phosphorus
Viscosity 1.3 cps	Thickness Coats 2200 Å at 3000 rpm	Shelf Life 20°C 3 months 4°C 9 months

Benefits

- Highest phosphorus doping level
- Easy shipping without POCl₃ complications
- Lower maintenance and cost of Ownership
- High purity materials
- Uniform Coatings
- Lower melting point than silica alone
- Stable processing independent of flow rates
- Available with impurity specification < 1 ppm range and also available <50 ppb range

Typical Application

This is a standard silicate phosphorous doped glass very typical for semiconductor applications. Typical curing at 150° - 200°C gives a low density but solid film. It continues to become increasingly dense as temperature increases to 300-650°C or higher. We recommend baking at the highest temperature the substrate will see in any post processing. For doping applications the glass is often removed after drive in. The phosphorous in the glass matrix can also act as a getter for sodium and other mobile ions. This reduces the effective concentration of unwanted ionic species in the semiconductor substrate.

Packaging

- 8 oz (240ml)
- 16 oz (500ml)
- Larger sizes available for high volume applications


Alternative Products

P-240
P-250
P-260
P-640

Alternate Elements to Add

- As
- Sb
- Blends of two or more elements are available
- Other elements available for compound semiconductor use

Spin-on-Glass P-280



Although all statements and information presented in this document are believed to be accurate and reliable, they are presented without warranty or guarantee of any kind, express or implied. Information presented does not relieve the end user from carrying out their own tests to determine suitability for use in their application. User assumes all risk and liability for product use or information and results obtained. Suggestions for use of material and processes are made without representation or warranty that any such is free from patent infringement and are not recommendations for patent infringement. Please see MSDS for information regarding health and safety of material use.